

Hz Acoustic Plaster 03



Areas of application



- Smooth, white plaster that retains its bright color for years.
- Can be tinted in most NCS and RAL colors.
- Suitable for wet zones.
- Can be made washable through impregnation.
- Easy to apply.
- Can be repaired and maintained.

Material base

Ready-to-use cellulose fiber-based acoustic plaster.

Storage

Must not be exposed to frost. Store at a minimum of +5 °C and a maximum of 30 °C, protected from direct sunlight. Shelf life of at least 12 months in tightly sealed original packaging.

Application

Hz Acoustic Plaster 03 can only be applied by certified installers or after training. It is compatible with multiple substrates - contact us for further details. The plaster is applied mechanically using spray equipment. Consult Hz Acoustic and follow the supplier's instructions.

Site conditions

The application and drying temperature must be between 15 °C and 22 °C. Humidity must not exceed 50 % RH due to drying requirements. Ensure good ventilation for optimal drying conditions.

Drying time

Approximately 1-2 days at 20 °C and a maximum of 50 % RH per layer.

Instructions

Safety information regarding transportation, storage, handling, and disposal can be found in the product's safety data sheet. The above recommendations, including specific suggestions for processing and using our product, are based on our knowledge and experience under normal conditions, assuming proper storage and application. Due to variations in materials, substrates, and working conditions, we cannot provide a general guarantee of outcome or adhesion. It is always the responsibility of the user to verify the product's suitability for the intended purpose.

Hz Acoustic Plaster 03



Specifications

Color	Standard white. Can be tinted in most NCS and RAL colors.
Package size	15 kg bucket. The bucket is made of 100 % recycled plastic.
Consumption	4.5 – 5.0 kg/m ²
MAL code (1993)	00 – 1
VOC content	EU VOC level: Category A/a/wb 30 g/l (2010) This product contains max 0 g/l VOC.
Fire classification	A2 – s1, d0 for the finished system on Hz Acoustic panels: 001, 001-R, 007, 007-R, 009, 009-R, 011, 011-R, 071 and 073. B – s1, d0 for the finished system on Hz Acoustic panels: 015, 017, 017-R, 019, 019-R, 021, 023 and 025.
pH value	Approx 9.0 – 10.0 at 20 °C
Working time (opening time)	Approx 15 min per m ² .
Drying time	Approx 1-2 days at 20 °C and max 50 % RH per layer.